Synthesis and Performance of $\text{Li}_2\text{MnSiO}_4$ as an Electrode Material for Hybrid Supercapacitor Applications

K. Karthikeyan, S. Amaresh, J.N. Son, and Y.S. Lee[†]

Faculty of Applied Chemical Engineering, Chonnam National University, Gwangju 500-757, Korea

ABSTRACT :

$\text{Li}_2\text{MnSiO}_4$ was synthesized using the solid-state method under an Ar atmosphere at three different calcination temperatures (900, 950, and 1000°C). The optimization of the carbon coating was also carried out using various molar concentrations of adipic acid as the carbon source. The XRD pattern confirmed that the resulting $\text{Li}_2\text{MnSiO}_4$ particles exhibited an orthorhombic structure with a $Pmn2_1$ space group. Cyclic voltammetry was utilized to investigate the capacitive behavior of $\text{Li}_2\text{MnSiO}_4$ along with activated carbon (AC) in a hybrid supercapacitor with a two-electrode cell configuration. The $\text{Li}_2\text{MnSiO}_4/\text{AC}$ cell exhibited a high discharge capacitance and energy density of 43.2 Fg^{-1} and 54 Whkg^{-1} , respectively, at 1.0 mAcm^{-2} . The $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor exhibited an excellent cycling stability over 1000 measured cycles with coulombic efficiency over > 99 %. Electrochemical impedance spectroscopy was conducted to corroborate the results that were obtained and described.

Keywords: Lithium manganese silicate, Activated carbon, Hybrid supercapacitors, Energy density, Specific capacitance

Received May 10, 2012 : Accepted June 8, 2012

1. Introduction

Recently, an increasing interest has been devoted to the development of supercapacitors because of their potential applications in many fields, such as hybrid electric vehicles (HEV), portable electronic devices, memory back-up systems, etc.¹⁾ Supercapacitors are classified into two main categories based on the storage mechanism utilized, namely, electric double-layer capacitors (EDLCs) and pseudo-capacitors. EDLCs with various types of carbon based materials have been used as electrodes in order to utilize the double-layer capacitance. On the other hand, pseudo-capacitors with transition metal oxides or conducting polymers have been used as electrodes in order to utilize the charge-transfer pseudo-capacitance. EDLCs offer

a high power density, a good reversibility and a long cycle life. Pseudo-capacitors have a much higher energy density and a lower cycle life than EDLCs. The hybridization of two types of electrodes to form a new capacitor called a hybrid supercapacitor is a unique approach that is used to enhance the energy density and the power density of a single cell. One of the electrodes is an energy source electrode (battery like electrodes) and the other terminal contains a power source electrode (either an EDLC or a pseudo capacitor electrode). The choice of the energy source electrode is also important because this electrode enhances the cell voltage (especially in lithium ion batteries) without sacrificing the energy and power densities.¹⁻⁵⁾

Numerous Li-ion intercalated host materials, such as LiFePO_4 , $\text{Li}_4\text{Ti}_5\text{O}_{12}$, LiMn_2O_4 , $\text{LiNi}_{1/3}\text{Co}_{1/3}\text{Mn}_{1/3}\text{O}_2$, $\text{Li}_4\text{Mn}_5\text{O}_{12}$, and LiCoO_2 , have been studied as electrode materials for hybrid supercapacitor applications.²⁻¹⁰⁾ Of the aforementioned energy source

[†]Corresponding author. Tel.: +82-62-530-1904
E-mail address: leeyys@chonnam.ac.kr

electrodes, the Mn based materials have attracted attention because they are environmentally benign and cost effective with higher operating voltages. Spinel LiMn_2O_4 has been extensively studied as an electrode material for hybrid supercapacitors. However, capacity fading was encountered in the 3 V regions during prolonged cycling because of the Jahn-Teller distortion that is associated with the average valence of manganese, which falls below +3.5 in LiMn_2O_4 . To overcome these issues, various metal ions, such as $\text{LiM}_x\text{Mn}_{2-x}\text{O}_4$ ($M = \text{Ni}, \text{Cr}, \text{and Co}$), have been used as substitutes and these new materials have been investigated as the cathodes for hybrid electrochemical devices.¹⁰ Nevertheless, the capacity fading has been minimized but not effectively prevented. Recently, a new family of lithium insertion hosts, i.e. Li_2MSiO_4 ($M = \text{Fe}, \text{Mn}, \text{Co}, \text{and Ni}$), has attracted the attention of researchers because of its appealing properties that include cell safety, extraction of more than one Li ion which offers the theoretical capacity $> 330 \text{ mAhg}^{-1}$, environmental friendliness, simple synthesis, and cost effectiveness. Orthosilicate group materials provide excellent thermal stability through strong Si-O bonding.¹¹⁻¹⁵ Due to said advantages, $\text{Li}_2\text{MnSiO}_4$ has been chosen as the energy source electrode in this study for the first time.

A reversible exchange of up to two lithium ions per formula unit (possible exploration of $\text{Mn}^{2+}/\text{Mn}^{3+}$ and $\text{Mn}^{3+}/\text{Mn}^{4+}$ redox couples) is feasible, provided that the above advantages are exhibited, and the structure of the compound is stable.¹¹⁻¹⁵ Previously, we firstly reported the silicates based supercapacitors with activated carbon (AC) electrodes in a conventional non-aqueous electrolyte (1 M LiPF_6 in ethylene carbonate (EC)/dimethyl carbonate (DMC) (1:1 vol./vol.)), which presents a superior cycle performance between 0.0-3.0 V at room temperature.¹⁶⁻¹⁷ In this study, we present the synthetic process and electrochemical properties of the $\text{Li}_2\text{MnSiO}_4$ material and cell performance of the $\text{Li}_2\text{MnSiO}_4$ /activated carbon (AC) electrode as a hybrid supercapacitor in more detail.

2. Experimental

The conventional solid-state reaction method was employed to prepare the $\text{Li}_2\text{MnSiO}_4$ powders. High purity $\text{LiOH}\cdot\text{H}_2\text{O}$ (Junsei 95 %), MnCO_3 (Aldrich, USA, 99.9 %), and SiO_2 (Aldrich, USA, 99.9 %) were used as the starting materials. Adipic acid (Aldrich,

Fig. 1. Schematic representation of the Synthesis of $\text{Li}_2\text{MnSiO}_4$ powder.

USA, 99 %) was used as the carbon source during the synthesis in order to improve the electric conductivity of the $\text{Li}_2\text{MnSiO}_4$ particles. Stoichiometric amounts of the starting materials were ground with adipic acid and heated at 400 °C for 4 h in air. The intermediate product was finely ground using a mortar and placed into a tubular furnace at different calcination temperatures (900, 950, and 1000 °C) for 12 h under an Ar atmosphere. The final calcination process was carried out to yield the $\text{Li}_2\text{MnSiO}_4$ powder. A similar procedure was repeated for the carbon coating with various concentrations of adipic acid (0, 0.05, 0.1, and 0.2 mol. adipic acid against the total metal ions present in the compound). The graphical representation of the optimized synthesis process is given in the Fig. 1.

The thermogravimetric-differential thermal analysis (TG/DTA) was conducted using a thermal analyzer system (STA 1640, Stanton Redcroft Inc., UK) at a rate of 5°Cmin^{-1} with a thin Pt plate that was used as the sample holder. The structural properties of $\text{Li}_2\text{MnSiO}_4$ were studied using an X-ray diffractometer (XRD, Rint 1000, Rigaku, Japan) with a $\text{Cu-K}\alpha$ radiation source. The morphological features were investigated using a scanning electron microscope (SEM, S-4700, Hitachi, Japan). The electrochemical profiles of the hybrid supercapacitor cell were obtained using a

CR 2032 coin cell at room temperature. The negative electrode was composed of 70% active materials ($\text{Li}_2\text{MnSiO}_4$), 20% conductive additive (ketjen black), and 10 % binder (teflonized acetylene black). The mixture was pressed on a 200 mm² stainless steel mesh that served as the current collector at a pressure of 300 kgcm⁻² and dried at 160°C for 4 h in an oven. The same procedure was adopted for the preparation of the positive electrode, i.e. the AC electrode. The cell was comprised of $\text{Li}_2\text{MnSiO}_4$ as the anode and an activated carbon as the cathode, and the two electrodes were separated by a porous polypropylene film (Celgard 3401). The electrolyte solution was 1.0 M LiPF_6 in an EC/DMC (1:1 v/v, Techno Semichem Co., Ltd, Korea) mixture. The cyclic voltammetry (CV) and the electrochemical impedance spectroscopy (EIS) studies were performed using an electrochemical analyzer (SP-150, Bio-Logic, France). The cycling studies were carried out between 0.0-3.0 V with a current density of 1.0 mAcm⁻² using a cycle tester (WBCS 3000, Won-A-Tech, Korea) in the galvanostatic mode.

3. Results and Discussion

Fig. 2 shows the thermogravimetric-differential thermal (TG-DTA) traces of the $\text{LiOH}\cdot\text{H}_2\text{O}$, MnCO_3 , and SiO_2 mixture. The thermal traces were recorded at 5°Cmin⁻¹ from 25 to 1000°C under an argon atmosphere. The thermogram clearly showed that multiple thermal events occurred during the analysis. The DTA curve showed two endothermic events below 120°C, and the corresponding weight loss was also observed

Fig. 2. Thermogravimetric-differential thermal (TG-DTA) traces of the $\text{LiOH}\cdot\text{H}_2\text{O}$, MnCO_3 , and SiO_2 starting materials.

in the TGA curve. The thermal events around 60°C and 100°C were caused by the removal of moisture during the loading of the sample and the dehydration of the water molecules in the starting materials, respectively. In the TG curve, a sharp weight loss (~20%) was observed between 300 and 380°C along with a gradual weight loss up to 720°C. The observed thermal events (weight losses) were probably caused by the decomposition of the carbonate moieties that were present in the starting materials.^{17,18)} Around 720°C, a small weight loss (~5%) was observed from the TG traces, corresponding to the formation of the $\text{Li}_2\text{MnSiO}_4$ phase.¹⁵⁾ Finally, a slow and continuous decrease in the weight of the mixture in the temperature range from 720-1000°C was ascribed to the solid-state reaction process. In this temperature range, the formation of highly crystalline $\text{Li}_2\text{MnSiO}_4$ and the existence of an inconspicuous thermal event were observed.

Fig. 3 represents the powder X-ray diffraction pattern of nanocrystalline $\text{Li}_2\text{MnSiO}_4$ at different calcination temperatures. These XRD patterns showed well developed, sharp, and intense peaks that reflected the crystalline nature of the synthesized $\text{Li}_2\text{MnSiO}_4$. The crystalline peaks were indicative of an orthorhombic structure with a $Pmn2_1$ space group. However, impurity phases, such as MnO, were unavoidably present in samples calcined at all three temperatures. Similar types of impurity phases were also exposed during the synthesis of $\text{Li}_2\text{MnSiO}_4$ powders using various other approaches.^{11-15,20)} Dompablo *et al.*²¹⁾ succeeded in preparing a $\text{Li}_2\text{MnSiO}_4$ material without MnO under

Fig. 3. X-ray diffraction pattern of $\text{Li}_2\text{MnSiO}_4$ powders prepared at three different temperatures: (a) 900, (b) 950, and (c) 1000°C.

various pressure conditions. At the same time, the formation of Mn_2SiO_3 was inevitable under these abnormal pressure conditions. Previous reports and the present study indicate that the preparation of phase pure $\text{Li}_2\text{MnSiO}_4$ powder is complicated. Based on the battery performance of the $\text{Li}_2\text{MnSiO}_4$ with different calcination temperatures, 900°C has been chosen for further characterization studies. The well known Debye-Scherrer formula was adopted for the calculation of the crystallite size at 900°C .

$$\delta = \frac{0.9\lambda}{\beta \cos\theta}$$

In this equation, δ is the crystallite size, λ is the X-ray wavelength ($\lambda = 1.54056 \text{ \AA}$), and β is the full width at the half maximum (FWHM) of the XRD peak. From this calculation, the mean size of the $\text{Li}_2\text{MnSiO}_4$ powders was about 500 nm .

The X-ray diffraction pattern of carbon coated $\text{Li}_2\text{MnSiO}_4$ compounds prepared by the solid-state reaction with different molar contents of AA is presented in Fig. 4. The orthosilicate groups were suffered from some disadvantages like inherent conducting properties, for instance $\text{Li}_2\text{MnSiO}_4$ ($\sim 10^{-14} \text{ Scm}^{-1}$) when compared to other commonly available candidates like LiCoO_2 ($\sim 10^{-4} \text{ Scm}^{-1}$), LiNiO_2 ($\sim 10^{-3} \text{ Scm}^{-1}$), LiMn_2O_4 ($\sim 10^{-6} \text{ Scm}^{-1}$) and LiFePO_4 ($\sim 10^{-9} \text{ Scm}^{-1}$) at room temperature.²²⁾ Further, the poor conductivity issue restricts the possibility of using orthosilicates in practical cells. A carbon coating is the

effective way to improve the electrochemical performance of the of the electrode materials, for example LiFePO_4 .^{23,24)} The source of carbon is also very important, particularly carboxylic ($-\text{COOH}-$) functional groups containing materials, for example carboxylic acids which act as the capping agent to prevent aggregation during synthesis. The choice of using adipic acid in the synthesis process is based on the successive carbon coating and excellent improvement of electrochemical performance of LiFePO_4 in both solid state and sol-gel routes by us.^{23,24)} Here, the same strategy has been applied to improve electrochemical performance of $\text{Li}_2\text{MnSiO}_4$ and the optimization of AA is performed based on the total metal ions present in the native compound. The calcination temperature was fixed at 900°C , which is based on the temperature optimization. The occurrence of broad and well-defined Bragg peaks demonstrated the formation of size controlled and highly crystallized $\text{Li}_2\text{MnSiO}_4$. All

Fig. 4. XRD patterns of $\text{Li}_2\text{MnSiO}_4$ obtained by various molar ratios of adipic acid to total metal ions: (a) 0, (b) 0.05, (c) 0.1, and (d) 0.2.

Fig. 5. Scanning electron microscope images of $\text{Li}_2\text{MnSiO}_4$ at 900°C . The molar ratio of adipic acid to total metal ions is 0.2.

XRD patterns of these materials obtained at various molar ratios of AA were well developed. Based on the optimization, 0.2 mol. AA containing $\text{Li}_2\text{MnSiO}_4$ exhibited the good lithium storage properties (not presented in this paper) when compared to rest of the concentrations and it composed of 0.52 wt % of carbon after the synthesis process. The presence of the impurity phase MnO is also noticed along with $\text{Li}_2\text{MnSiO}_4$. Appearances of satellite peaks in the X-ray diffraction pattern are indicative of an orthorhombic structure, which is analogous to the Li_3PO_4 pattern. The $\text{Li}_2\text{MnSiO}_4$ can be isostructural to certain forms of Li_3PO_4 : Mn^{2+} ions are present within a $[\text{SiO}_4]$ anionic silicate network that replaces $[\text{PO}_4]$ the anionic phosphate network, and two Li ions are available in 3D dimensional channels. Further, we believe, the strong Si-O bond translates into very stable electrochemical and thermal properties, which are important for safety.

The morphological features of the synthesized $\text{Li}_2\text{MnSiO}_4$ at 900°C with 0.2 mol. AA were analyzed using scanning electron microscopy (SEM) and presented in Fig. 5. The SEM image results signified the uneven size (sub-micrometer) and surface morphology of the $\text{Li}_2\text{MnSiO}_4$ particles that were synthesized using the solid-state reaction method. Furthermore, the appearance of small-sized particles was also observed along with the larger-sized particles. The SEM study correlated well with the crystallite size that was obtained from the Debye-Scherrer calculations using the XRD measurements.

The electrochemical characterizations were performed using the cyclic voltammetry (CV) analysis

method with a two-electrode cell configuration. The CV was an appropriate tool for estimating the difference the Faradaic and non-Faradaic reaction processes.²⁵⁾ Furthermore, this technique was also used to determine the preliminary power and energy densities of the supercapacitors. Fig. 6 shows the steady state cyclic voltammograms of the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor that were obtained from a potential window of between 0.0-3.0 V at various scanning rates ranging from 1 to 25 mV s^{-1} . The shapes of the CV traces showed that the current responses depended on the scanning rate. Additionally, the voltammograms maintained an almost rectangular shape with a mirror image even at higher scanning rates, which corresponds to excellent capacitive behavior for the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor. The CV traces overlapped at increased scanning rates. This overlapping effect showed that two different energy storage mechanisms were involved in the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor.^{4,26)} The surface charge accumulated at the electrode/electrolyte interface (activated carbon electrodes), and the Faradaic electron transfer reaction and reversible phase transformation occurred during the Li^+ ion intercalation reaction ($\text{Li}_2\text{MnSiO}_4$ electrode).²²⁾

The cycling performance of the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor was directly measured using the galvanostatic mode between 0.0-3.0 V with a constant current rate of 1 mAcm^{-2} at room temperature. The capacitance (F) of the hybrid cell was calculated using the following equation, $C_{\text{cell}} = I \cdot t / V$, where I is the current density (mAcm^{-2}), t is the discharge time (s), and C_{cell} is the total capacitance (F). The discharge capacitance (Fg^{-1}) was calculated using $C_s = 4C_{\text{cell}}/M$, where M is the total weight (g) of the two electrode materials used except for the current collectors.^{26,27)} In Fig. 7(a), the discharge curves of the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor were symmetric with respect to their charge counterpart, and the slopes of every curve were almost independent of the potential, with the same discharge capacity. An ohmic drop occurred during the discharge process because of the lower electronic conductivity of $\text{Li}_2\text{MnSiO}_4$. This $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor exhibited a discharge capacitance (C_s) of 43.2 Fg^{-1} during the first cycle, and an almost equivalent capacity was maintained thereafter. Fig. 7(b) represents the cycling profiles of the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor with respect to the coulombic efficiency at a current rate of 1 mAcm^{-2} .

Fig. 6. Cyclic voltammogram of the $\text{Li}_2\text{MnSiO}_4/\text{activated carbon}$ hybrid supercapacitor at various scanning rates: (a) 1 mVs^{-1} , (b) 3 mVs^{-1} , (c) 15 mVs^{-1} , and (d) 25 mVs^{-1} .

Fig. 7. (a) Charge-discharge curves of the $\text{Li}_2\text{MnSiO}_4/\text{activated carbon}$ hybrid supercapacitor at 1 mAcm^{-2} . (b) Discharge capacitance and coulombic efficiency as a function of the cycle number.

Fig. 8. (a) Energy and power densities with respect to different current densities. (b) Specific capacitance vs. cycle number of the $\text{Li}_2\text{MnSiO}_4/\text{activated carbon}$ hybrid supercapacitor (the values in the figures correspond to the current densities in mAcm^{-2}).

The $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor exhibited an excellent cycling stability over 1000 measured cycles with an excellent coulombic efficiency of over 99%. The good cycling stability of the novel $\text{Li}_2\text{MnSiO}_4$ electrode that was utilized in the hybrid supercapacitor complemented the intrinsic stability of the AC electrode. Usually, the cycle life of a $\text{Li}_2\text{MnSiO}_4$ electrode mainly depends on the operating rates and depth-of-discharge, which determine the available energy and power densities.²⁵⁾

Rate performance studies were carried out for the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor. Current densities ranging from 1 to 10 mAcm^{-2} were used for the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor at room temperature. Initially, the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor was cycled 1000 times at 1 mAcm^{-2} and subjected to various current rates from 2 to 10 mAcm^{-2} for 250 cycles each. The energy and power densities corresponding to these current rates are graphically illustrated in Fig. 8(a). The energy and power densities

were calculated for the initial cycle of each current rate that was applied. As expected, the power density linearly varied with respect to the current rates. However, the discharge capacitance and energy density gradually decreased from 43.2 Fg^{-1} to 29.6 Fg^{-1} and from 54 to 37 Whkg^{-1} , respectively, as the current density increased from 1 to 10 mAcm^{-2} (Fig. 8(b)). The variations in the specific capacitance were ascribed to the large ohmic drop, which led to small capacitance values, and the activation and concentration polarizations at higher current densities, which resulted in the low utilization of the active materials.^{4,26)} At high current rates, the lithium ions do not have enough time to enter into the core of the material which also causes the reduction in discharge capacitance values.²⁶⁾

Electrochemical impedance spectroscopy (EIS) was employed in order to obtain information about the supercapacitor performance. Fig. 9 shows a typical Nyquist plot for the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid superca-

Fig. 9. Nyquist plot of the $\text{Li}_2\text{MnSiO}_4/\text{activated carbon}$ hybrid supercapacitor cell.

pacitor cell at an open circuit voltage in the frequency range of 100 MHz to 100 mHz. From the Nyquist plot, the first intersection point on the real axis of the spectrum in the high frequency region corresponded to the bulk solution resistance of the electrolyte (R_s). After R_s , a semicircle appeared with a second intersection point on the real axis at medium frequencies. In this region of high frequency to medium frequencies, called the kinetic control regime, only small amounts of electron transfer overcame the activation energy in order to migrate with the alternating potential. Furthermore, the semicircle developed moving across the Helmholtz plane, and was represented by the interfacial contact capacitance (C_c) and charge transfer resistance (R_c). In the adequately low frequency range, the constantly decreasing frequency provided enough time for the charge-complexes in the diffusion layer to overcome the activation energy and move closer to the Helmholtz plane. These charge-transfers ultimately occupied all of the available surfaces of the AC electrodes and contributed to the electrical double layer capacitance (C_{dl}). The low frequency range, where C_{dl} contributed, is called the diffusion control regime. A capacitance value of 40 Fg^{-1} was obtained from the Nyquist plot for the hybrid cell using the following relationship, $C = -1/2\pi fZ''m$, where f , Z'' , and m are the frequency, the impedance of the imaginary component, and the mass of the active material, respectively. Generally, the EIS measurements give rise to slightly lower capacitance values than the cycling studies because the alternating current penetrates into the electrode bulk with more hindrance.³⁰⁾

4. Conclusion

Novel $\text{Li}_2\text{MnSiO}_4$ material was synthesized at three different calcinations temperatures under an Ar atmosphere using a solid-state reaction method. The XRD patterns confirmed that the synthesized $\text{Li}_2\text{MnSiO}_4$ particles exhibited an orthorhombic structure with a $Pmn2_1$ space group. The crystallite size of the $\text{Li}_2\text{MnSiO}_4$ particles lied in the submicrometer range and was correlated with SEM and Scherrer analysis. The capacitive performance of the $\text{Li}_2\text{MnSiO}_4$ electrode was substantiated through cyclic voltammetry with an activated carbon electrode in a single cell. The cycling stability of the $\text{Li}_2\text{MnSiO}_4/\text{AC}$ hybrid supercapacitor was investigated over 2250 cycles galvanostatically. The $\text{Li}_2\text{MnSiO}_4/\text{AC}$ cell exhibited discharge capacitances of 43.2 and 29.6 Fg^{-1} and energy densities of 54 and 37 Whkg^{-1} at low (1 mAcm^{-2}) and high (10 mAcm^{-2}) current rates, respectively.

Acknowledgements

This work was supported by the Priority Research Centers Program through the National Research Foundation of Korea (NRF) funded by the Ministry of Education, Science and Technology (2009-0094058).

References

1. B. E. Conway, *Electrochemical Supercapacitors*, Kluwer-Plenum, New York (1999).
2. Y. Zhang, H. Feng, X. Wu, L. Wang, A. Zhang, T. Xia, H. Dong, X. Li, and L. Zhang, *Int. J. Hydrogen Energ.*, **34**, 4889-4899 (2009).
3. P. Simon and Y. Gogosti, *Nat. Mater.*, **7**, 845-854 (2008).
4. I. Plitz, A. Dupasquier, F. Badway, J. Gural, N. Pereira, A. Gmitter, and G. G. Amatucci, *Appl. Phys. A.*, **82**, 615-626 (2006).
5. A. S. Arico, P. G. Bruce, B. Scrosati, J. M. Tarascon, and W. V. Schalkwijk, *Nat. Mater.*, **4**, 366-377 (2005).
6. X. L. Wu, L. Y. Jiang, F. F. Cao, Y. G. Guo, and L. J. Wan, *Adv. Mater.*, **21**, 2710-2714 (2009).
7. Y. G. Wang, J. Y. Lou, W. Wu, C. X. Wang and Y. Y. Xia, *J. Electrochem. Soc.*, **154** (2007) A228-A234.
8. A. D. Pasquier, A. Laforge, and P. Simon, *J. Power Sources.*, **125**, 95-102 (2004).
9. J. Y. Luo, J. L. Liu, P. He, and Y.-Y. Xia, *Electrochim. Acta.*, **53**, 8128-8133 (2008).
10. H. Wu, C. V. Rao, and B. Rambabu, *Mater. Chem. Phys.*, **116**, 532-535 (2009).
11. A. Nytén, A. Abouimrane, M. Armand, T. Gustafsson, and J. O. Thomas, *Electrochem. Commun.*, **7**, 156-160

- (2005).
12. R. Dominko, M. Bele, M. Gabersček, A. Meden, M. Remškar, and J. Jamnik, *Electrochem. Commun.*, 8, 217-222 (2006).
 13. A. Kokalj, R. Dominko, G. Mali, A. Meden, M. Gaberscek, and J. Jamnik, *Chem. Mater.*, 19, 3633-3640 (2007).
 14. R. Dominko, *J. Power Sources.*, 184, 462-468 (2008).
 15. W. Liu, Y. Xu, and R. Yang, *J. Alloys Comp*, 480, L1-L4 (2009).
 16. K. Karthikeyan, V. Aravindan, S. B. Lee, I. C. Jang, H. H. Lim, G. J. Park, M. Yoshio, and Y. S. Lee, *J. Power Sources*, 195, 3761-3764 (2010).
 17. K. Karthikeyan, V. Aravindan, S. B. Lee, I. C. Jang, H. H. Lim, G. J. Park, M. Yoshio, and Y. S. Lee, *J. Alloys Comp*, 504, 224-227 (2009).
 18. L. X. Yang, Y. J. Zhu, H. Tong, and W. W. Wang, *Ultrason. Sonochem.*, 14, 259-265 (2007).
 19. X. H. Hu, X. P. Ai, H. X. Yang, and S. X. Li, *J. Power Sources.*, 74, 240-243 (1998).
 20. R. Dominko, I. Arcon, A. Kodre, D. Hanzel, and M. Gaberscek, *J. Power Sources.*, 189, 51-58 (2009).
 21. M. E. A. Dompablo, R. Dominko, J. M. G. Amores, L. Dupont, G. Mali, H. Ehrenberg, J. Jamnik, and E. Moran, *Chem. Mater.*, 20, 5574-5584 (2008).
 22. M. Park, X. Zhang, M. Chung, G. B. Less, A. M. Sastry, *J. Power Sources* (DOI: 10.1016/j.jpowsour.2010.06.060).
 23. H. H. Lim, I. C. Jang, S. B. Lee, K. Karthikeyan, V. Aravindan, and Y. S. Lee, *J. Alloys Compds*, 495, 181-184 (2010).
 24. S. B. Lee, I. C. Jang, H. H. Lim, V. Aravindan, H. S. Kim, and Y. S. Lee, *J. Alloys Compds*, 491, 668-671 (2010).
 25. Q. Wang, Z. Wen, and J. Li, *Adv. Func. Mater.*, 16, 2141-2146 (2006).
 26. G. G. Amatucci, F. Badway, A. D. Pasquier, and T. Zheng, *J. Electrochem. Soc.*, 148, A930-A939 (2001).
 27. J. H. Park and O. O. Park, *J. Power Sources.*, 111, 185-190 (2002).
 28. V. Khomenko, E. R. Pinero, and F. Beguin, *J. Power Sources.*, 153, 183-190 (2006).
 29. K. Zaghib, J. B. Goodenough, A. Mauger, and C. Julien, *J. Power Sources.*, 194, 1021-1023 (2009).
 30. W. Xing, S. Z. Qiao, R. G. Ding, F. Li, G. Q. Lu, Z. F. Yan, and H.M. Cheng, *Carbon*, 44, 216-224 (2006).