Remarkable Stability of Graphene/Ni-Al Layered Double Hydroxide Hybrid Composites for Electrochemical Capacitor Electrodes

Jeong Woo Lee^a, Su-Il In^b, and Jong-Duk Kim^{a,†}

^aDepartment of Chemical and Biomolecular Engineering, Center for Energy and Environment Engineering, Korea Advanced Institute of Science and Technology (KAIST), Daejeon 305-701, Republic of Korea

^bDepartment of Energy Systems Engineering, Daegu Gyeongbuk Institute of Science and Technology (DGIST), Daegu 711-873, Republic of Korea

ABSTRACT:

Graphene/Ni-Al layered double hydroxide (LDH) hybrid materials were synthesized by a hydrothermal reaction. Hexagonal Ni-Al LDH particles nucleated and grew on graphene sheets, thus preventing restacking of the graphene sheets and aggregation of the Ni-Al LDH nanoparticles upon drying. Electrode made from the graphene/Ni-Al LDH hybrid materials showed a substantial improvement in electrochemical capacitance relative to those made with pure Ni-Al LDH nanoparticles. In addition, the graphene/Ni-Al LDH hybrid composite materials showed remarkable stability after 4000 cycles with over 100% capacitance retention. These materials are thus very promising for use in electrochemical capacitor electrodes.

Keywords: Graphene, Ni-Al layered double hydroxide, Electrochemical capacitors

Received March 4, 2013 : Accepted March 24, 2013

1. Introduction

The growing energy needs of the global economy, combined with concerns about the environmental and geopolitical impact of increasing fossil fuel use, are driving a 21st century revolution in green energy materials. Electrochemical capacitors or supercapacitors have received increasing attention as next-generation devices for backup, transportation and other power-intensive applications.¹⁾ Carbon-based supercapacitors are characterized by high power density and long cycle life. Various types of metal hydroxides,²⁾ metal oxides,³⁾ and polymers⁴⁾ have been reported with high energy density arising from redox reactions, but due to their limited conductivity they typically have low power density and poor cyclability. Composites of carbon materials and metal oxides combine the high energy density of metal oxides with the high conduc-

tivity of carbon, and thus can have a synergistic effect for electrochemical capacitor applications.

Among carbon materials, graphene and graphene oxide have recently emerged as especially promising materials. Two-dimensional sheets of graphene have high electric conductivity,⁵⁾ optical transparency,⁶⁾ and elasticity.⁷⁾ Individual sheets of graphene can be prepared by simple mechanical exfoliation of graphite (the scotch tape method), but this method is not easily scaled to bulk quantities.⁸⁾ Macroscopic amount of graphene can be obtained by reaction of exfoliated graphite oxide with strong reducing agents such as hydrazine or sodium borohydride. However, the graphene sheets tend to restack in this process because of the strong van der Waals force and of π - π stacking. An effective strategy for preventing the loss of surface area upon restacking is to co-precipitate a metal oxide *in situ*. Many papers about graphene/metal oxide composites including graphene/Ni(OH)₂,⁹⁾ graphene/layered double hydroxide,¹⁰⁾ graphene/Co(OH)₂,¹¹⁾ graphene/RuO₂,¹²⁾ graphene/MnO₂,¹³⁾ and graphene/

[†]Corresponding author. Tel.: +82-42-350-3921

E-mail address: jdkim@kaist.ac.kr

Co_3O_4 ¹⁴⁾ have taken advantage of this strategy for energy storage devices.

Layered double hydroxides (LDHs) are composed of positively charged metal hydroxide layers separated by charge-balancing anions and intercalated water molecules.¹⁵⁾ LDHs can be represented by a general formula $\text{M}^{2+}_{1-x}\text{M}^{3+}_x(\text{OH})_2(\text{A}^{m-})_{x/m}\cdot n\text{H}_2\text{O}$, where M^{2+} is Mg^{2+} , Ni^{2+} , Ca^{2+} , Co^{2+} , Cu^{2+} , Zn^{2+} , or Cd^{2+} and M^{3+} is Fe^{3+} , Al^{3+} , or Cr^{3+} . A is a counter ion with $-m$ charge. The most typical anions are Cl^- , NO_3^- , SO_4^{2-} , CO_3^{2-} , OCN^- , and CH_3COO^- . In recent years, LDHs have received attention due to their diverse applications as photocatalysts,¹⁶⁾ bioactive nanocomposites,¹⁷⁾ and electrochemical capacitors.^{18,19)}

Recently, we reported hierarchical microspheres composed of wrinkled α -Ni(OH)₂ nanosheets²⁾ and graphene/ α -Ni(OH)₂ hybrid composites.⁹⁾ While α -Ni(OH)₂ showed high initial capacitance, it degraded rapidly because of the instability of the α -Ni(OH)₂ phase. In this study, to stabilize α -Ni(OH)₂ as an electroactive Ni–Al LDH, some of the Ni^{2+} was substituted by Al^{3+} . Ni–Al LDH nanoparticles were nucleated and grown on graphene sheets in a hydrothermal reaction. When an appropriate mass ratio of transition metal oxide or hydroxide and graphene is used, graphene-based composites normally show high specific capacitance.^{9,11)} A series of graphene/Ni–Al LDH hybrid composites (GNA) with different mass ratios were analyzed by the cyclic voltammetry and galvanostatic charging-discharging methods in order to optimize their electrochemical properties. The resulting graphene/Ni–Al LDH hybrid composites showed remarkable stability over 4000 cycles without degradation of the capacitance.

2. Experimental Section

2.1. Synthesis of samples

Graphite oxide (GO) was obtained from natural graphite (Sigma-Aldrich) using the modified Hummers method as in previous reports.²⁰⁾ GO was exfoliated in water by ultrasonication. The concentration of the resulting graphene oxide dispersion was 0.9 mg/mL. For GNA-1, the graphene oxide dispersion (80 mL) was reduced to graphene dispersion with the use of ammonium hydroxide (1 mL) and hydrazine hydrate (1 mL) in an oil bath at 95°C for 2 h. After the reaction, the graphene dispersion was filtered, washed with water several times, and redispersed in 80 mL of

water. $\text{NiSO}_4\cdot 6\text{H}_2\text{O}$ (2 mmol) and $\text{Al}_2(\text{SO}_4)_3\cdot 18\text{H}_2\text{O}$ (0.5 mmol) were dissolved in the graphene dispersion and the pH was subsequently set to 10.5 by addition of ammonium hydroxide (about 15 wt%) with vigorous magnetic stirring. The solution was transferred into a Teflon-lined autoclave. The autoclave was heated to 180°C for 12 h. After the reaction, the autoclave was cooled naturally to room temperature. A precipitate was washed with excess water, and dried by lyophilization. GNA-2 was synthesized in the same manner using 4 mmol of $\text{NiSO}_4\cdot 6\text{H}_2\text{O}$ and 1 mmol of $\text{Al}_2(\text{SO}_4)_3\cdot 18\text{H}_2\text{O}$. Pure Ni–Al LDH and reduced graphene oxide (rGO) were also obtained by the same procedure for comparison.

2.2. Sample characterization

X-Ray Diffraction (XRD) analysis was performed on a Philips X'Pert MPD powder X-ray diffractometer (Cu K α , 40 kV, 40 mA). Raman spectra were obtained using a LabRAM HR UV/vis/NIR (Horiba Jobin Yvon, France) with an Ar ion CW laser (514.5 nm) as an excitation source. Fourier transform infrared spectroscopy (FTIR) was carried out on an IFS66V/S & HYPERION 3000 spectrometer (Bruker Optics, Germany). X-ray photoelectron spectroscopy (XPS) spectra were recorded with a Thermo VG Scientific Sigma Probe spectrometer. Transmission electron microscopy (TEM) images were taken on a JEOL 2010F.

2.3. Preparation of electrodes

To evaluate the electrochemical properties of GNA hybrid composites, working electrodes were prepared as follows: GNA hybrid composites, carbon black as a conducting material, and polyvinylidene fluoride (PVdF) as a binder were mixed in a weight ratio of 85:10:5, respectively, using N-methyl-2-pyrrolidone (NMP) as the solvent, yielding a paste. This paste was incorporated into nickel foam (1 × 1 cm). The mass of active materials in the working electrode was 2 mg. Working electrodes prepared in this way were dried at room temperature for 1 day, and then in a vacuum oven for 1 day, in that order.

2.4. Evaluation of electrochemical properties

Electrochemical studies were carried out by measurement of cyclic voltammetry (CV) and galvanostatic charging-discharging of half cells using an EZStat potentiostat/galvanostat (Nuvant Systems Inc.). A beaker type three-electrode cell was equipped

with the GNA hybrid composite on nickel foam working electrode, an Ag/AgCl electrode (BASi) reference electrode, and platinum wire as a counter electrode. For all electrochemical characterization experiments, 1 M KOH was used as the electrolyte solution at ambient temperature. The specific capacitance was calculated by integrating the area under the CV curve to obtain the charge (Q) and then dividing by the mass of electroactive material (m), the scan rate (v) and the potential window ($\Delta V = V_a - V_c$) according to following equation:

$$C = \frac{Q}{\Delta V} = \frac{1}{mv(V_a - V_c)} \int_{V_a}^{V_c} I(V) dV \quad (1)$$

In addition, the specific capacitance can be calculated from the galvanostatic charging-discharging function according to Eq. (2):

$$C = \frac{I \times \Delta t}{\Delta V \times m} \quad (2)$$

In this equation, C is specific capacitance, I is the current, Δt is the discharging time, ΔV is the potential window, and m is mass of electroactive material.

3. Results and Discussion

The synthetic route to GNA hybrid composites are shown schematically in Fig. 1. A graphene dispersion reduced by hydrazine was used as the precursor for synthesis of GNA hybrid composites. Subsequently,

nickel and aluminum salts were dissolved in the graphene dispersion solution, and Ni–Al LDH nanoparticles were precipitated by addition of base. In a subsequent hydrothermal reaction, Ni–Al LDH hexagonal plates were nucleated and grew on the dispersed graphene sheets.

The XRD patterns of GO, rGO, Ni–Al LDH, and GNA-2 are shown in Fig. 2. In the case of GO, a strong peak at 10.3° was found, corresponding to the (002) reflection of graphite oxide. This corresponding d-spacing (0.86 nm) is much larger than that of pristine graphite (0.34 nm) due to the introduction of oxygen-containing functional groups on the basal plane of the carbon sheets and intercalation of water. For rGO prepared by reduction with hydrazine, weak reflection at 24° and 42° (0.37 and 0.21 nm) were observed, indicating that graphite oxide was reduced to partially restacked graphite. The XRD pattern of the Ni–Al LDH nanoparticles shows (003), (006), (012), (015), and (110) reflections, which are similar to those observed in earlier reports.²¹⁾ For GNA-2, the XRD pattern was similar to that of pure Ni–Al LDH, which indicates that the graphene/Ni–Al LDH hybrid composites contains nanocrystalline inclusion of that phase.

Raman spectroscopy can be used to assess the degree of crystallinity of carbonaceous materials. Raman spectra of GO and GNA-2 are shown in Fig. 3. The spectra show two broad peaks at 1350 and 1590 cm^{-1} in both samples, attributed to the D and G

Fig. 1. Schematic representation of the steps in the synthesis of graphene/Ni–Al LDH hybrid composites.

Fig. 2. XRD patterns of GO, rGO, Ni-Al LDH, and GNA-2.

Fig. 3. Raman spectra of GO, rGO, and GNA-2.

band, respectively. The D band at 1350 cm^{-1} arises from the breathing mode of κ -point phonons with A_{1g} symmetry and the G band at 1590 cm^{-1} is assigned to the E_{2g} phonon of sp^2 carbon.²²⁾ The peak intensity ratio of the D and G band (I_D/I_G) was used to determine the degree of order and average size of the sp^2 domains. The intensity ratio for GNA-2 and rGO is increased relative to that of GO, which indicates greater disorder, possibly due to the formation of localized sp^3 defects within the sp^2 carbon network during reduction of GO.²³⁾

The reduction of the oxygen-containing functional groups of GO and the formation of Ni-Al LDH are clearly analyzed by the FT-IR spectra (Fig. 4). The GO shows multiple peaks in the range of $1000\text{--}1750\text{ cm}^{-1}$, indicating that oxygen-containing functional groups are founded such as hydroxyl, epoxy, carbonyl, and carboxyl groups.²⁴⁾ In addition, a broad band at

Fig. 4. FT-IR spectra of GO, rGO, Ni-Al LDH, and GNA-2.

3450 cm^{-1} can be observed, corresponding to the O-H vibration of graphene oxide. After reduction, these peaks disappear. Also, the band at 1587 cm^{-1} , which can be ascribed to the skeletal vibration of the graphene sheets, appears during the reduction process of graphene oxide to graphene by hydrazine.²⁵⁾ The FT-IR spectra of Ni-Al LDH and GNA-2 are similar to each other, although the bands attributed to the LDH phase are stronger in the former. A broad peak around 3450 cm^{-1} can be assigned to O-H groups in transition metal hydroxides.²⁶⁾ The broad band around 1640 cm^{-1} is assigned to the $\delta\text{H}_2\text{O}$ vibration of water molecules intercalated between Ni-Al LDH layers.²⁾ The band at 1140 cm^{-1} is assigned to SO_4^{2-} ions in the interlayer space of Ni-Al LDH.²⁾ Bands at 1340 cm^{-1} can be assigned to the presence of CO_3^{2-} ions formed from atmospheric CO_2 , as the positively charged Ni-Al LDH layers have a strong affinity for CO_3^{2-} ions.²⁷⁾

Complementary information about the surface chemical composition of the graphene/Ni-Al LDH composites can be obtained from XPS spectra, which are shown in Fig. 5. For GNA-2, a survey scan ($0\text{--}1200\text{ eV}$) shows mainly carbon (C 1s), oxygen (O 1s), nickel (Ni 2p), aluminum (Al 2p), sulfur (S 2p), and oxygen (O 1s) species. Deconvolution of the C 1s peak of GNA-2 shows different oxygen functional groups of non-oxygenated C at 284.5 eV , carbon in C-O at 285.7 eV , carbonyl carbon ($\text{C}=\text{O}$) at 286.6 eV , and carboxylate carbon ($\text{O}-\text{C}=\text{O}$) at 289.1 eV . The intensities of these peaks are smaller than in GO, consistent with reduction of GO. In the Ni 2p region ($850\text{--}890\text{ eV}$), the 2p spectrum shows Ni $2p_{1/2}$ and Ni $2p_{3/2}$ as well as their satellites. The binding energies of Ni

Fig. 5. XPS spectra of (a-b) GO and (c-d) GNA-2.

$2p_{2/3}$, Ni $2p_{2/3}$ (s), Ni $2p_{1/2}$, and Ni $2p_{1/2}$ (s) are 856.3, 862.1, 874.0, and 879.4 eV, respectively, consistent with spectra of Ni–Al LDH.²⁸⁾ A very weak S 2p was observed at 168.5 eV, which can be explained by the fact that SO_4^{2-} ions are intercalated into the interlamellar space of Ni–Al LDH, which was also indicated by FT-IR.

To elucidate the morphology and structure of the graphene/Ni–Al LDH composites, a TEM analysis was conducted. TEM images of GNA-1 were shown in Fig. 6(a). Hexagonal plates of crystalline Ni–Al LDH particles decorate the larger graphene sheets. The lateral sizes of the Ni–Al LDH crystals are 50–200 nm. The synthesis of Ni–Al LDH as hexagonal

plates by the slow and continuous hydrolysis of urea in a hydrothermal reaction has been reported.²¹⁾ This study shows that the coprecipitation method with ammonium hydroxide followed by a hydrothermal reaction yields very similar hexagonal Ni–Al LDH particles. The particle size of Ni–Al LDH in GNA-1 is similar to that of free Ni–Al LDH (Fig. 6(b)).

Electrochemical properties of Ni–Al LDH, GNA-1, and GNA-2 determined by CV and galvanostatic charging-discharging methods. Fig. 7 shows CV curves of pure Ni–Al LDH, GNA-1, and GNA-2 at a scan rate of 5 mV/s. All CV curves have two peaks. One peak is anodic (positive current density) corresponding to the oxidation of Ni^{2+} to Ni^{3+} , and the other

Fig. 6. TEM images of (a) GNA-1 and (b) pure Ni–Al LDH.

Fig. 7. (a) CV curves of pure Ni-Al LDH, GNA-1, and GNA-2 at 5 mV/s scan rate and (b) corresponding specific capacitance.

is cathodic (negative current density) during the reverse process. These peaks come from fast and reversible redox processes that occur at the interface of Ni-Al LDH and the KOH electrolyte. These reactions can be represented by Eq. (3):

Since the specific capacitance is proportional to the area under CV curve, this quantity was determined through a comparison of CV curves. The area under the CV curves at 5 mV/s scan rate increased in the order of pure Ni-Al LDH < GNA-1 < GNA-2, and

corresponding specific capacitances were 210, 565, and 710 F/g, respectively.

Galvanostatic charging-discharging is complementary method for measuring the specific capacitance of electrochemical capacitors at constant current density. Fig. 8(a)-(c) show the galvanostatic discharge curves of Ni-Al LDH, GNA-1, and GNA-2, and their corresponding specific capacitances are plotted in Fig. 8(d). The specific capacitances increase in the order of Ni-Al LDH < GNA-1 < GNA-2, consistent with the CV measurements. For GNA-2, the specific capacitance under 1, 2, 5, and 10 A/g current density was 1523, 1265, 900, and 710 F/g, respectively.

Fig. 8. Galvanostatic discharge curves of (a) Ni-Al LDH, (b) GNA-1, and (c) GNA-2 at current densities of 1, 2, 5, and 10 A/g, and (d) corresponding capacitance at current densities of 1, 2, 5, and 10 A/g.

Fig. 9. Cycle testing of GNA-2: galvanostatic charging-discharging curve at a nominal charging rate of 5 A/g and the variation in the specific capacitance as function of cycle number.

The specific capacitance of the GNA hybrid materials was, as expected, higher than that of pure Ni–Al LDH. The difference may be attributed to two factors. First, the graphene sheets in the GNA composites impart higher electronic conductivity, and thus a greater fraction of the Ni sites are accessible for the fast Faradaic redox reactions of Ni^{2+} and Ni^{3+} . The second factor is the dispersion of the Ni–Al LDH crystals on the graphene sheets. The intimate mixing of the two phase prevents the restacking of graphene sheets and thus preserves electrolyte accessibility to the Ni–Al LDH phase.

Endurance tests of GNA-2 were carried out by galvanostatic charging-discharging at 10 A/g, which is a very high current density for electrochemical capacitors (Fig. 9). The capacitance increased slightly in the initial 100 cycles and was then maintained at 100% until 4000 cycles. The initial increase can be ascribed to activation of a small fraction of the Ni–Al particles. By comparison, we recently reported the high capacitance of graphene/ α -Ni(OH) $_2$, but the retention of capacitance was only 12.1% after 500 cycles.⁹⁾ α -Ni(OH) $_2$ is known for its high capacitance, but it is not a suitable material for long cycle performance due to phase instability.^{2,9)} Hybrid composites with Ni–Al LDH and graphene yield very high capacitance as well as extraordinary capacitance retention.

4. Conclusion

In summary, hexagonal Ni–Al LDH plates were

nucleated and grown on graphene sheets in a hydrothermal reaction. The unstable α -Ni(OH) $_2$ phase previously studied is stabilized by partially substituting Al^{3+} ions for Ni^{2+} ions to form Ni–Al LDH. The graphene sheets in GNA hybrid composites impart higher electronic conductivity, and the Ni–Al LDH particles inhibit re-stacking of the graphene sheets, thus promoting electrolyte access to the electroactive Ni–Al LDH plates. The specific capacitance of the GNA hybrid composites was dramatically higher than that of pure Ni–Al LDH crystals, and showed remarkable stability after a brief break-in period with 100% capacitance retention over 4000 cycles. These composite materials are thus potentially very good candidates for electrochemical capacitor applications.

Acknowledgment

This work was supported by the BK 21 program.

References

1. A. S. Arico, P. Bruce, B. Scrosati, J. M. Tarascon and W. V. Schalkwijk, *Nat. Mater.* **1**, 366 (2005).
2. J. W. Lee, J. M. Ko and J.-D. Kim, *J. Phys. Chem. C* **115**, 10445 (2011).
3. J. W. Lee, T. Ahn, J. H. Kim, J.M. Ko and J.-D. Kim, *Electrochim. Acta* **56**, 4849 (2011).
4. R. Y. Song, J. H. Park, S. R. Sivakkumar, S. H. Kim, J. M. Ko, D. Y. Park, S. M. Jo and D. Y. Kim, *J. Power Sources* **166**, 297 (2007).
5. J. N. Hu, X. L. Ruan and Y. P. Chen, *Nano Lett.* **9**, 2730 (2009).
6. C. Li, Z. Li, H. Zhu, K. Wang, J. Wei, X. Li, P. Sun, H. Zhang and D. Wu, *J. Phys. Chem. C* **114**, 14008 (2010).
7. Q. He, S. Wu, S. Gao, X. Cao, Z. Yin, H. Li, P. Chen and H. Zhang, *ACS Nano* **5**, 5038 (2011).
8. Y. Zhu, S. Murali, W. Cai, X. Li, J. W. Suk, J. R. Potts and R. S. Ruoff, *Adv. Mater.* **22**, 3906 (2010).
9. J. W. Lee, T. Ahn, S. Devaraj, J. M. Ko and J.-D. Kim, *Chem. Commun.* **47**, 6305 (2011).
10. L. Wang, D. Wang, X. Y. Dong, Z. J. Zhang, X. F. Pei, X. J. Chen, B. Chen and J. Jin, *Chem. Commun.* **47**, 3556 (2011).
11. S. Chen, J. Zhu and X. Wang, *J. Phys. Chem. C* **114**, 11829 (2010).
12. Z. S. Wu, D. W. Wang, W. Ren, J. Zhao, G. Zhou, F. Li and H. M. Cheng, *Adv. Funct. Mater.* **20**, 3595 (2010).
13. J. Yan, Z. Fan, T. Wei, W. Qian, M. Zhang and F. Wei, *Carbon* **48**, 3825 (2010).
14. H. Yan, T. Wei, W. Qiao, B. Chao, Q. Zhao, L. J. Zhang and Z. Fan, *Electrochim. Acta* **55**, 6973 (2010).
15. A. I. Khan and D. O'Hare, *J. Mater. Chem.* **12**, 3191

- (2002).
16. C. G. Sivia, Y. Bouizi, V. Fones and H. Garcia, *J. Am. Chem. Soc.* **131**, 13833 (2009).
 17. J. H. Choy, S. Y. Kwak, J. S. Park, Y. J. Jeong and J. Protier, *J. Am. Chem. Soc.* **121**, 1399 (1999).
 18. Y. Wang, W. Yang, C. Chen and D. G. Evans, *J. Power Sources* **184**, 682 (2008).
 19. M. A. Woo, M. S. Song, T. W. Kim, I. Y. Kim, J. Y. Ju, Y. S. Lee, S. J. Kim, J. H. Choy and S. J. Hwang, *J. Mater. Chem.* **21**, 4286 (2011).
 20. W. S. Hummers and R. E. Offeman, *J. Am. Chem. Soc.* **80**, 1339 (1958).
 21. Z. Liu, R. Ma, Y. Ebina, N. Iyi, K. Takada and T. Sasaki, *Langmuir* **23**, 861 (2007).
 22. Y. Zhou, Q. Bao, L. A. L. Tang, Y. Zhong and K. P. Loh, *Chem. Mater.* **21**, 2950 (2009).
 23. S. Stankovich, D. A. Dikin, R. D. Piner, K. A. Kohlhaas, A. Kleinhammes, Y. Jia, Y. Wu, S. T. Nguyen and R. S. Ruoff, *Carbon* **45**, 1558 (2007).
 24. P. G. Ren, D. X. Yan, X. Ji, T. Chen and Z. M. Li, *Nanotechnology* **22**, 055705 (2011).
 25. C. Nethravathi and M. Rajamathi, *Carbon* **46**, 1994 (2008).
 26. J. W. Lee, W. C. Choi and J.-D. Kim, *CrystEngComm* **12**, 3249 (2010).
 27. Z. Liu, R. Ma, M. Osada, K. Takada and T. Sasaki, *J. Am. Chem. Soc.* **127**, 13869 (2005).
 28. M. Wei, X. Xu, X. Wang, F. Li, H. Zhang, Y. Lu, M. Pu, D. G. Evans and X. Duan, *Eur. J. Inorg. Chem.* **14**, 2831 (2006).