Investigation of Lithium Transference Number in PMMA Composite Polymer Electrolytes Using Monte Carlo (MC) Simulation and Recurrence Relation

Renwei Eric Koh*, Cha Chee Sun, Yee Ling Yap, Pei Ling Cheang, and Ah Heng You

Faculty of Engineering and Technology, Multimedia University, 75450 Melaka, Malaysia

ABSTRACT

In this study, Monte Carlo (MC) simulation is conducted with recurrence relation to study the effect of SiO₂ with different particle size and their roles in enhancing the ionic conductivity and lithium transference number of PMMA composite polymer electrolytes (CPEs). The MC simulated ionic conductivity is verified with the measurements from Electrochemical Impedance Spectroscopy (EIS). Then, the lithium transference number of CPEs is calculated using recurrence relation with the MC simulated current density and the reference transference number obtained. Incorporation of micron-size SiO₂ ($\leq 10\ \mu\text{m}$) fillers into the mixture improves the ionic conductivity from $8.60 \times 10^{-5}\ \text{S/cm}$ to $2.35 \times 10^{-4}\ \text{S/cm}$. The improvement is also observed on the lithium transference number, where it increases from 0.088 to 0.3757. Furthermore, the addition of nano-sized SiO₂ ($\leq 12\ \text{nm}$) fillers further increases the ionic conductivity up towards $3.79 \times 10^{-4}\ \text{S/cm}$ and lithium transference number of 0.4105. The large effective surface area of SiO₂ fillers is responsible for the improvement in ionic conductivity and the transference number in PMMA composite polymer electrolytes.

Keywords : Solid Polymer Electrolytes, Monte Carlo Simulation, Transference Number, Recurrence Relation, Ionic Conductivity

Received : 21 September 2020, Accepted : 3 November 2020

1. Introduction

Solid Polymer Electrolytes (SPE's) are electrolytes in solid form which consist of dissolved inorganic salts as charge carriers. SPEs eliminated the need for a separator. As a result, it is safer than traditional liquid and gel electrolytes. Besides, SPEs are extremely flexible and had better compatibility with most electrode materials. However, the application of SPEs on energy powered devices is hindered due to their high degree of crystallinity at room temperature. Due to the higher degree of crystallinity in traditional polymer electrolytes, i.e. PEO based polymer electrolytes, the motion on Li⁺ ions among the polymer chain is stalled, and this causes the film to generate a significant amount of internal resistance that

results in low ionic conductivity and lithium transference number. Agrawal *et al.* [1] reported an ionic conductivity of $1 \times 10^{-7}\ \text{S/cm}$ for PEO-LiClO₄ at room temperature in their study of solid polymer electrolytes system. Also, Pozyczka *et al.* [2] reported a lithium transference number of 0.054 to 0.059 for PEO-LiTFSI SPEs with a molar ratio of 6:1 at 70°. Ionic conductivity and lithium transference number reported in the above studies for PEO SPEs are insufficient for practical application [3].

Moreover, ion transport in polymer electrolytes is a temperature-dependent process [4], ions received energy via thermal vibration to overcome the energy barrier so that they can have enough activation energy to hop to a nearby open vacant site. Thus, low activation energy and availability of open bond is essential for ionic transport in SPEs. Nevertheless, ionic conductivity and lithium transference numbers in SPEs can be boosted via the addition of ionic salts, plasticizers, and ceramic fillers [5-7].

Qian *et al.* [8] reported an improvement in ionic conductivity from $1.30 \times 10^{-7}\ \text{S/cm}$ for (PEO)₁₆LiClO₄

*E-mail address: 1142701349@student.mmu.edu.my

DOI: <https://doi.org/10.33961/jecst.2020.01459>

This is an open-access article distributed under the terms of the Creative Commons Attribution Non-Commercial License (<http://creativecommons.org/licenses/by-nc/4.0>) which permits unrestricted non-commercial use, distribution, and reproduction in any medium, provided the original work is properly cited.

to 2.36×10^{-4} S/cm at room temperature when 50 wt% Ethylene Carbonate (EC) was incorporated into the mixture. The addition of plasticizers lowers the glass transition temperature, T_g of the mixture, and this decreases the degree of crystallinity of polymer electrolytes at room temperature. As a result, the segmental motion of the polymer chain is enhanced, and the ionic conductivity increases. Xiao *et al.* [9] reported improvement in lithium transference numbers when ZrO_2 particles were added into P(VDF-HFP)-PMMA matrix to create composite polymer electrolytes. They obtain lithium transference number of 0.28 to 0.41 for P(VDF-HFP)-PMMA- ZrO_2 composite polymer electrolytes, an improvement from 0.16 without the addition of ZrO_2 particles. The improvement in lithium transference number can be related to the large effective area of ZrO_2 particles. The larger effective area provides Li^+ ions more conduction pathways in the polymer matrix, this improves the dynamic of the polymer chain, thus yielding higher lithium transference number.

Although improving the performance of SPEs is an area of intense interest of many researchers, but there is not much attention paid in understanding the ionic transport mechanism in SPEs using particle simulation. Furthermore, the random behaviour of ions in the free volume also makes studying the transportation characteristics and conduction phenomenon of ions in polymer electrolytes challenging. Dynamic Bond Percolation (DBP) is one of the earliest models that describe ions motion in a statistically disordered and dynamically rearranging medium [10]. Not until Wagner *et al.* [11] introduced Monte Carlo (MC) model, a three-dimensional model for thermally activated ion transportation in a multi-well energy structure.

In this work, a stochastic Monte Carlo method using random sampling technique is employed to develop a model capable of study SPEs with minimal needs of experiment. PMMA is used as the host polymer and LiCF_3SO_3 as the dopant salt. The advantages of using LiCF_3SO_3 as the dopant salt are because of its resistance to oxidation, lower activation energy and, non-toxicity [7]. Besides, larger anion radius of LiCF_3SO_3 ensure a higher degree of dissociation of salt in the polymer matrix, this ensures better segmental mobility and yielding higher ionic conductivity [7,12]. Furthermore, PMMA as a semi-crystalline polymer is selected as the polymer host because of its

higher ionic conductivity and lithium transference number at room temperature compared to traditional PEO based system that are suffering from low ionic conductivity and transference number at room temperature due to their high degree of crystallinity [13,14]. Several studies also show that PMMA based polymer electrolytes have the potential to be fabricated into solid electrolytes used in solid-state batteries and solid-state supercapacitors [15-17].

MC simulations are used to study the effect of SiO_2 fillers with different filler sizes on the ionic conductivity, and the transference number of PMMA- LiCF_3SO_3 system is calculated using recurrence relation. The simulation results are then compared to the measurement data to ensure the validity of the model.

2. Measurement and simulation of ionic conductivity and transference number

2.1 Sample preparation and characterization

The samples were prepared using solution cast method [14,18]. Poly(methyl-methacrylate) (PMMA), Ethylene Carbonate (EC), Lithium Triflate (LiCF_3SO_3), and Silicon Dioxide (SiO_2) in the experiment are obtained from Sigma Aldrich. PMMA (Mw – 996,000) were mixed the plasticizers, LiCF_3SO_3 and SiO_2 inorganic fillers to yield a two-gram mixture. The mixture is first dissolved in Tetrahydrofuran (THF) solution and stirred using a magnetic stirrer until a homogenous solution is obtained. The homogenous solution was then poured into petri dishes and kept in a desiccator for drying until dry electrolyte films were obtained. Lastly, the films are cut into smaller samples, and the thickness of each sample was measured using micro-meter screw gauges and assembled into the battery cell for testing.

Gamry reference 600 series potentiostat was used for Electrochemical Impedance Spectroscopy (EIS) to characterize the polymer electrolytes samples. EIS is conducted in the frequency ranging from 0.1Hz to 1MHz at room temperature with the sample sandwiched between two spring-loaded stainless-steel electrodes, and the ionic conductivity is calculated by using the following equation:

$$\sigma = \frac{t}{R_B A} \quad (1)$$

where t (cm) is the thickness of SPE film, R_B is the bulk resistance of electrolyte obtained from the

Nyquist plot, and A (cm^2) is the contact area between the film and the electrode, which equates to 2.56 cm^2 in this work.

DC polarization measurement was also performed using Gamry reference 600 series potentiostat using a polarization voltage of 20mV to obtain the initial current, I_o and steady-state current, I_s . The transference number is calculated using Bruce-Vincent equation [19].

$$t_+ = \frac{I_s(\Delta V - I_o R_o)}{I_o(\Delta V - I_s R_s)} \quad (2)$$

where ΔV is the polarization voltage, R_o and R_s are the resistance before and after polarization consisting of charge transfer resistance and passivating film resistance.

2.2 Monte Carlo Simulation

Interpreting the dynamics of ion in a dynamically disordered system like SPE is not an easy task as ions interact with each other in a polymer lattice, which is continually evolving with time. Nevertheless, by using MC simulation, it enables us to study the dynamic properties of ions by treating this complicated system as a grouping of many single ions. Hopping is the primary ion transport mechanism in a polymer. When an electric field was presence, Li^+ ions start to drift; once the ions receive enough activation energy to overcome the energy barrier height and there was a free bond, the ions will hop to a nearby vacant site. In this study, the mass of Li^+ ions was set to be $1.1525 \times 10^{-26} \text{ kg}$ and the electric field will be the moving force of the Li^+ ions. The free-flight time and hopping events will be generated using a random number generator with a value of between 0 and 1. The wave vector, $\vec{k}_x$ in the direction of the applied electric field will be selected at the beginning of the simulation as the initial condition of Li^+ ions. The distance of Li^+ ions travelled can be determined by:

$$l = d \frac{\sqrt{p}}{(1-p)} \quad (3)$$

where d represents the lattice spacing and p is the probability of observing an open bond at a nearby vacant site. The probability p is generated using a random number generator, $0 \leq p \leq 1$, corresponding to the randomly appeared open bond in a polymer chain segment. The way of the ions transport in the

polymer chain is known as “hopping.” Basically, ions that received enough energy to overcome the energy barrier height will hop to a nearby open bond, and it is a thermally activated process given by [4]:

$$s = v_o \exp \left[-\frac{(E_i - E_f)}{kT} \right] \quad (4)$$

, where $(E_i - E_f)$ is the energy barrier height, v_o is the escaping frequency of Li^+ ions, T is the temperature in Kelvin, k represents the Boltzmann constant, E_i and E_f are the energy of the ions before and after hopping, respectively. The activation energy is set to be ($< 0.2 \text{ eV}$) as it was appropriate for SPEs [20]. The motion of Li^+ ions is simulated to occur randomly within a time frame from t to $t + 0.01 \text{ ps}$ with their position updated every 0.01 ps . The wave vector obtained from the drifting process will be transferred to the hopping process for the verification of the hopping mechanism of Li^+ ions and the state of Li^+ ions after the hopping event. With all the parameters at hand, the drift velocity of Li^+ v , mobility μ under the influence of electric field E using the following equation:

$$\mu = \frac{v}{E} \quad (5)$$

With mobility of ions obtained, the electric field dependent conductivity is calculated using:

$$\sigma = nq\mu \quad (6)$$

, where n represents the concentration of ions, q is the total number of charged transferred by ions, and μ is the mobility of ions. The current density, J is then calculated using Ohm's law:

$$J = \sigma E \quad (7)$$

3. Recurrence Relation

The lithium transference number is defined as the number of moles of lithium-ion transferred for one Faraday of charge transferred. In polymer electrolytes, the cation transference number is obtained by dividing the cation number over the number of ions transport across the cell. Current is the product due to transportation of Li^+ ions. As such, the lithium transference number is determined using the ratio of steady-state current over the initial current in SPE.

In this work, the lithium transference number of PMMA SPEs is obtained using recurrence relation and the simulated current density. The transference number, t_{+si} is derived based on recurrence relation developed by Matsuo et al. [21] and the steady-state current method introduced by Evans *et al.* [19]. Also, the initial and steady-state current densities in MC simulation are obtained through Ramo's theorem [22].

The current density is given by $i(t) = qv/d$, where v represents the charge velocity, q is the amount of charge transferred, and d is the separation distance. The reference lithium transference number, t_{+si} of PMMA-LiCF₃SO₃-EC is calculated as [19]:

$$t_{+si} = \frac{I_{ss(ref)}}{I_o} \quad (8)$$

, where I_o and $I_{ss(ref)}$ is the measured initial and reference current densities for plasticized PMMA polymer electrolytes. $I_{ss(ref)}$ is used as reference current density for obtaining lithium transference number in PMMA-EC-LiCF₃SO₃-SiO₂ using recurrence relation. The lithium transference number of PMMA-EC-LiCF₃SO₃-SiO₂ is calculated as:

$$t_{+si} = \left(1 + \frac{I_{ssi}}{I_{ss(ref)}}\right)t_{+ref} \quad (9)$$

When more than one composition is incorporated into the mixture, this equation can be generalized using the recurrence relation, in which lithium transference number for various composition in polymer electrolytes is given as:

$$t_{+si} = \left(1 + \sum_{i=1}^{\infty} \frac{I_{ssi}}{I_{ss(ref)}}\right)t_{+ref} \quad (10)$$

, where I_{ssi} is the steady-state current density in PMMA-LiCF₃SO₃-EC with different sizes of SiO₂ fillers, $I_{ss(ref)}$ is the steady-state current density in PMMA-LiCF₃SO₃-EC, and t_{+ref} is the lithium transference number of PMMA-LiCF₃SO₃-EC sample.

It is similar to the general expression of recurrence equation, $y_1 = (1 + a_0 \sum_{i=1}^{\infty} x_{i-1})b_0$, where $a_0 = \frac{1}{I_{ss(ref)}}$

and $b_0 = t_{+ref}$. The unity describes the mobile Li⁺ ions successfully travelling through the electrolyte by overcoming the barriers in the solid polymer electrolytes.

In this work, the ionic conductivity and steady-state current density of PMMA-LiCF₃SO₃-EC-SiO₂ are simulated using MC simulation, and the lithium transference number is calculated using recurrence relation, based on the ratio of MC simulated steady-state current density by using lithium transference number of PMMA-LiCF₃SO₃-EC as reference. The results obtained are compared with experimental results and data from various works of literature.

4. Results and Discussion

4.1 Ionic Conductivity of SPEs

Fig. 1 shows the Nyquist of PMMA-LiCF₃SO₃-EC SPE film at 27°C. The bulk resistance, R_b is determined from the Nyquist plot with a value of 97.93Ω. Experimental measurements for PMMA-LiCF₃SO₃-EC, PMMA-LiCF₃SO₃-EC-SiO₂ (≤10μm), and PMMA-LiCF₃SO₃-EC-SiO₂ (≤12nm) is tabulated in Table 1. The ionic conductivity obtained via MC simulation is shown in Fig. 2, and results from MC simulation agree well with experimentally obtained data.

Fig. 1. Nyquist plot of PMMA-LiCF₃SO₃-EC at room temperature and its equivalent circuit (inset).

Table 1. Ionic conductivity values from measurements

SPE Sample	Sample Composition	Ionic Conductivity (S/cm)	Number of ions
PMMA 1	PMMA-LiCF ₃ SO ₃ -EC	8.60×10^{-5}	8.50×10^{10}
PMMA 2	PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤10μm)	2.35×10^{-4}	2.30×10^{11}
PMMA 3	PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤12nm)	3.79×10^{-4}	3.80×10^{11}

Fig. 2. Monte Carlo ionic conductivity simulation of PMMA 1 (dash-dot line), PMMA 2 (dash line), and PMMA 3 (solid line) SPE samples.

It is shown that PMMA1 sample which does not contain ceramic filler has the lowest conductivity of 8.60×10^{-5} S/cm, a value comparable to work from Pal *et al.* [23], where they reported a conductivity of 3.52×10^{-5} S/cm for plasticized PMMA-LiClO₄. The low ionic conductivity is mainly contributed by the crystallinity nature of PMMA at room temperature, where Li⁺ ions are believed to suffering from low mobility and are trapped within the polymer chain.

With the addition of SiO₂ ($\leq 10\mu\text{m}$), ionic conductivity of 2.35×10^{-4} S/cm is achieved for PMMA2 sample. Chew *et al.* [24] also reported an improvement in ionic conductivity when they added micron size SiO₂ particles into PMMA based polymer electrolytes. They reported an ionic conductivity of 2.15×10^{-4} S/cm for PMMA-LiCF₃SO₃-EC-SiO₂, an improvement from 1.36×10^{-5} S/cm without SiO₂ fillers in their study.

In this study, nano-sized SiO₂ filler is also added into the polymer matrix. The addition of nano-sized filler further increases the ionic conductivity up to 3.79×10^{-4} S/cm for PMMA3 samples. The improvement in ionic conductivity agrees well with [25,26] findings where conductivity enhancement increases with increasing effective surface area of filler grains, as nano-sized SiO₂ has a greater surface area than micron-sized SiO₂ fillers. The improvement in ionic conductivity is associated with the increase in conduction pathway benefitted from the larger effective surface area of SiO₂ particles.

Moreover, the addition of SiO₂ fillers disrupts the crystal structure of PMMA matrix. As a result, it low-

ers the ionic attraction force and improves Li⁺ ions chain mobility. Dissanayake *et al.* [25] studied the effect of particle size on the ionic conductivity of PEO based polymer electrolytes. They reported the conductivity was significantly improved with the smallest filler size having the larger effective surface area. By decreasing the particle size from $10\mu\text{m}$ to 10nm , ionic conductivity was increased by one order of magnitude at 70°C .

Furthermore, the improvement in ions mobility is also verified through MC simulation. Results from simulation show an increase in the number of ions travelling through the polymer, from 8.50×10^{10} for PMMA1 samples up to 3.80×10^{11} for PMMA3 samples. The increasing number of ions travelling through the polymer is directly related to the mobility improvement of Li⁺ ions, since there are more space and larger free volume in the polymer matrix for Li⁺ ions to travel around more easily [25,27].

4.2 Transference number calculation using recurrence relation

Fig. 3 shows the dc polarization curve for PMMA1 samples, the lithium transference number is calculated using Bruce-Vincent method developed by Bruce *et al.* [19], and it is found to be 0.088. The obtained lithium transference number for PMMA1 samples is used as a reference for the calculation of lithium transference number for PMMA2 and PMMA3 samples by using recurrence relation and MC simulation obtained current density. Fig. 4 compares the experimentally obtained steady-state current density with MC simulated current density under

Fig. 3. DC polarization curve for PMMA-LiCF₃SO₃-EC with an applied dc voltage of 20 mV.

Fig. 4. Steady-state current density of PMMA SPEs with and without SiO₂ fillers (dashed line: MC simulation, dotted: Measurements).

an electric field of 10 V/m for PMMA1, PMMA2, and PMMA3 samples, respectively.

It is known that cations are responsible for the generation of electricity inside the battery, and the current density produced is dependent on the ionic conductivity of SPE inside the battery. As a result, PMMA1 samples that have the lowest ionic conductivity produces the lowest current density of 0.0214 μA/cm², and the ionic conductivity increases up to 0.0703 μA/cm² for PMMA 2 samples with the

addition of SiO₂ (≤10 μm). The highest current density of 0.0758 μA/cm² is obtained for PMMA3 samples that exhibit the maximum ionic conductivity. With the current density obtained from all samples and lithium transference number for PMMA1 samples, the lithium transference number for PMMA2 and PMMA3 samples are calculated using recurrence relation. Table 2 shows the transference number of PMMA-LiCF₃SO₃-EC solid polymer electrolytes with and without SiO₂ fillers.

Table 3 shows the lithium transference obtained in this work compared to the lithium transference number obtain from other literature, and it is shown that the lithium transference number obtained using recurrence relation is reasonable. The highest lithium transference number obtained in this study is 0.4105 for PMMA-LiCF₃SO₃-EC-SiO₂ (≤ 12 nm), which is comparable to lithium transference number reported by Xiao *et al.* [9] in their study of P(VDF-HFP)-PMMA hybrid polymer electrolytes doped with ZrO₂ particles. Furthermore, Liu *et al.* [28] reported a maximum lithium transference number of 0.39 for PEO CPEs doped with Ga-LLZO nanofillers. Wang *et al.* [29] and Liu *et al.* [30] obtained lithium transference number of up to 0.54 and 0.56 respectively in their study of PEO gel polymer electrolytes (GPEs) doped

Table 2. Lithium transference number calculated using recurrence relation

Sample ID	Sample Composition	Current Density (μA/cm ²)	Lithium transference number (t ⁺)
PMMA 1	PMMA-LiCF ₃ SO ₃ -EC	0.0215	0.088
PMMA 2	PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤ 10 μm)	0.0703	0.3757
PMMA 3	PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤ 12 nm)	0.0788	0.4105

Table 3. Lithium transference number obtained in this work compared to other researchers.

Composition	Type	Reference	t ⁺
PMMA-LiCF ₃ SO ₃ -EC	Solid	This work	0.088
PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤ 10 μm)	Solid	This work	0.3757
PMMA-LiCF ₃ SO ₃ -EC-SiO ₂ (≤ 12 nm)	Solid	This work	0.4105
PEO-PVP-LiNO ₃	Solid	Jinisha [20]	0.332
P(VDF-HFP)-PMMA-LiPF ₆ -EC-ZrO ₂	Solid	Xiao [9]	0.28 - 0.41
P(VDF-HFP)-PMMA-LiPF ₆ -EC	Solid	Xiao [9]	0.16
PEO-LiCF ₃ SO ₃ -EC-SiO ₂ (≤ 12 nm)	Gel	Wang [29]	0.54
PEO-LiBF ₄ -EC-SiO ₂ (≤ 12 nm)	Gel	Liu [30]	0.34-0.56
PMMA-LiBOB-EC	Gel	Hosseinioun [31]	0.34
PMMA-LiClO ₄ -EC	Gel	Faridi [13]	0.39 - 0.42

with SiO₂ nano-particles. Naturally, lithium transference number obtained for GPEs would be higher than that of SPEs, because GPEs are more amorphous than SPEs, and the mobility of Li⁺ ions in GPEs is higher, yielding a higher lithium transference number.

5. Conclusion

A sophisticated MC model had been developed in this study, the model is capable of simulating the ionic conductivity of PMMA-LiCF₃SO₃-EC of various compositions at room temperature, and the simulation data agree well with experimental results. The results also illustrate that PMMA CPEs with SiO₂ particles greatly enhance the ionic conductivity and lithium transference number in comparison with the traditional SPEs at room temperature. Since cations are the primary charge carriers in the system, the enhancement in ionic conductivity produces higher current density and larger cationic transference number. The highest ionic conductivity and current density achieved at room temperature in this work are 3.79×10^{-4} S/cm and $0.0788 \mu\text{A}/\text{cm}^2$, respectively, for PMMA-LiCF₃SO₃-EC-SiO₂ (≤ 12 nm). The highest lithium transference number recorded is 0.4105 with $3.8 \times 10^{11} \text{ cm}^{-3}$ Li⁺ ions travelling through the PMMA polymer electrolyte for nano-sized SiO₂ particles in the simulation. Lastly, it is shown that the addition of inorganic particle into the polymer matrix greatly enhances the ionic conductivity and lithium transference number of traditional electrolytes system. CPEs not only has a greater ionic conductivity and lithium transference number than traditional polymer electrolytes system, but several recent studies also show that CPEs exhibit better thermal stability and energy density [16,32].

Declaring of Competing Interest

I hereby declare that I have no competing financial interest or personal relationship that could have appeared to influence the work reported in this paper.

Acknowledgement

This work is supported by FRGS/ 2019, Ministry of Higher Education, Malaysia.

Reference

- [1] R. C. Agrawal, G. P. Pandey, *J. Phys. D. Appl. Phys.*, **2008**, 22(41), 223001.
- [2] K. Pożyczka, M. Marzantowicz, J. R. Dygas, F. Krok, *Electrochim. Acta.*, **2017**, 227, 127-135.
- [3] S. Li, S. Q. Zhang, L. Shen, Q. Liu, J. B. Ma, W. Lv, Y. B. He, Q. H. Yang, *Adv. Sci.*, **2020**, 7(5), 1903088.
- [4] R. C. Agrawal, R. K. Gupta, *J. Mater. Sci.*, **1999**, 34(6), 1131-1162.
- [5] L. R. A. K. Bandara, M. A. K. L. Dissanayake, B. Mellander, *Electrochim. Acta.*, **1998**, 43(10-11), 1447-1451.
- [6] M. Forsyth, D. R. MacFarlane, A. Best, J. Adebahr, P. Jacobsson, A. J. Hill, *Solid State Ionics.*, **2002**, 147(3-4), 203-211.
- [7] L. Sampath Kumar, P. Christopher Selvin, S. Selvasekarapandian, *Polym. Bull.*, **2020**.
- [8] X. Qian, N. Gu, Z. Cheng, X. Yang, E. Wang, S. Dong, *Mater. Chem. Phys.*, **2002**, 74(1), 98-103.
- [9] W. Xiao, Z.Y. Wang, Y. Zhang, R. Fang, Z. Yuan, C. Miao, X. Yan, Y. Jiang, *J. Power Sources.*, **2018**, 382, 128-134.
- [10] S. D. Druger, M. A. Rather, A. Nitzan, *Solid State Ionics.*, **1983**, 9, 1115-1120.
- [11] A. Wagner, H. Kliem, *J. Appl. Phys.*, **2002**, 91(10), 6638-6649.
- [12] Sudaryanto, E. Yulianti, H. Jodi, *Polym Plast Technol Eng.*, **2015**, 54(3), 290-295.
- [13] M. Faridi, L. Naji, S. Kazemifard, N. Pourali, *Chem. Pap.*, **2018**, 72(9), 2289-2300.
- [14] C. C. Sun, A. H. You, L. L. Teo, *J. Polym. Eng.*, **2019**, 39(7), 612-619.
- [15] S. Kurapati, S. S. Gunturi, K. J. Nadella, H. Erothu, *Polym. Bull.*, **2019**, 76(10), 5463-5481.
- [16] Y. S. Lim, H. A. Jung, H. Hwang, *Energies.*, **2018**, 11(10), 2559-2569.
- [17] I. Zakariya'u, B. Gultekin, V. Singh, P. K. Singh, *High Perform Polym.*, **2020**, 32(2), 201-207.
- [18] Y. L. Yap, A. H. You, L. L. Teo, *Ionics.*, **2019**, 25(7), 3087-3098.
- [19] J. Evans, C. A. Vincent, P. G. Bruce, *Polymer.*, **1987**, 28(13), 2324-2328.
- [20] B. Jinisha, K. M. Anilkumar, M. Manoj, V. S. Pradeep, S. Jayalekshmi, *Electrochim. Acta.*, **2017**, 235, 210-222.
- [21] K. Matsuo, M. C. Teich, B. E. A. Saleh, *J. Light. Technol.*, **1985**, 3(6), 1223-1231.
- [22] S. Ramo, *Proceedings of the IRE.*, **1939**, 27(9), 584-585.
- [23] P. Pal, A. Ghosh, *Solid State Ionics.*, **2018**, 319, 117-124.
- [24] K. W. Chew, K. W. Tan, *Int. J. Electrochem. Sci.*, **2011**, 6(11), 5792-5801.
- [25] M. A. K. L. Dissanayake, P. A. R. D. Jayatilaka, R. S. P. Bokalawala, I. Albinsson, B. E. Mellander, *J. Power Sources.*, **2003**, 119, 409-414.
- [26] H. M. J. C. Pitawala, M. A. K. L. Dissanayake, V. A. Seneviratne, *Solid State Ionics.*, **2007**, 178(13-14), 885-

- 888.
- [27] G. B. Appetecchi, F. Croce, B. Scrosati, *J. Power Sources.*, **1997**, *66*(1-2), 77-82.
- [28] Z. Li, H. M. Huang, J. K. Zhu, J. F. Wu, H. Yang, L. Wei, X. Guo, *ACS Appl. Mater. Interfaces.*, **2019**, *11*(1), 784-791.
- [29] W. Wang, P. Alexandridis, *Polymers.*, **2016**, *8*(11), 387.
- [30] Y. Liu, J. Y. Lee, L. Hong, *J. Power Sources.*, **2004**, *129*(2), 303-311.
- [31] A. Hosseinioun, P. Nürnberg, M. Schönhoff, D. Diddens, E. Paillard, *RSC Adv.*, **2019**, *9*(47), 27574-27582.
- [32] P. Yao, H. Yu, Z. Ding, Y. Liu, J. Lu, M. Lavorgna, J. Wu, X. Liu, *Front. Chem.*, **2019**, *7*, 552.